Coating e film funzionali e biobased applicati ai prodotti cellulosici: ricerche nel contesto regionale ed europeo

Maria Beatrice Coltelli,
Dipartimento di Ingegneria Civile ed Industriale,
Università di Pisa

Biomateriali: la natura ama i compositi...

ALTA DISPONIBILITA'

BIOMATERIALI
POLISSACCARIDICI
PER APPLICAZIONI
STRUTTURALI

legno: micro-composito di cellulosa in resina a base di lignina

Esoscheletro degli artropodi: micro-composito di fibre di chitina in una matrice proteica (containing also calcium carbonate)

Struttura dell'esoscheletro degli artropodi

struttura

Legame ad idrogeno inter-macromolecolare

Ogni nano-fibrilla di chitina è composta di circa 20 catene lineari di poli(N-acetil glucosammina)

Il materiale rigido risultante a base di chitina è immerso in una matrice di proteina e carbonato di calcio

PURIFICAZIONE DELLA CHITINA

Tattamento acido

Tattamento basico

Grado di acetilazione 0,9 e peso molecolare nell'intervallo $1-2,5 \cdot 10^6$

MNV Ravi Kumar, React. Funct. Polym, 46, 2000, 1-27

microfibre

Chitina e chitosano:
Disponibilità di 10 miliardi di tonnellate l'anno

N. Van Toan, The Open Biomaterials Journal, 1, 2009

Le microfibre contengono nano-fibre cristalline. E' possibile produrre nano-fibrille di chitina per trattamento chimico delle microfibre

L'impianto di MAVI SUD presso Aprilia (Roma), ha brevettato questo processo e lo ha applicato principalmente a chitina proveniente da rifiuti di crostacei proveniente dai paesi baltici. Le nanofibrille di chitina sono disponibili in sospensione acquosa diluita per applicazioni cosmetiche

*P. Morganti, in
Nanofabrication using
nanomaterials, Ch 1*

Lunghe 300 nm e
larghe 10 nm

PROPRIETÀ DELLE NANOFIBRILLE DI CHITINA (CN)

- Proprietà anti-microbiche basate sulla capacità di stimolare le difese immunitarie delle cellule
- Proprietà rigenerative per la pelle dimostrate sulle ustioni della pelle
- Possono essere usate come carrier, sfruttando la capacità di coordinarsi con nanoparticelle caricate negativamente, intrappolando così molecole funzionali

Applicazione di sospensioni di CN sul cartoncino

INNOCARTOPACK, cassa di Risparmio di Lucca

Components

Chitin dispersion

plasticizer

Chitosan powder

Acidic solution

Fig. 1 Mixing process

Fig. 2 Chitosan-chitin mixtures. a) mainly chitin b) mainly chitosan

Preparazione di soluzioni lievemente acide contenenti CN e chitosano per trattare cartoncini vergini o riciclati

- a → principalmente CN
- b → principalmente chitosano

Mechanical tests

Table 2 Tensile test results. Stress at break (σ_b) and percentage strain at break (ϵ_b) are reported

Film sample	σ_b (MPa)	ϵ_b (%)
C80G5	22,62±5,22	4,35±2,03
C80G15	25,18±5,83	4,87±1,30
C80G20	14,06±4,75	10,13±9,36
C80G30	12,45±4,80	63,45±10,37
C20G5	9,09±1,08	10,20±3,83
C20G15	6,16±2,41	14,70±3,45
C20G30	3,41±0,34	37,4±5,43

Fig.4 Tensile test of C80G30 film

B
A

Fig.5 Films were prepared from the mixtures by solution casting method.

riciclato

vergine

	Bending M (mN)	Bending C (mN)
virgin	370	160
Based on chitin (brush)	400	220
Based on chitosan (bar)	380	210
recycled	265	125
Based on chitosan (bar) 60°	400	200

$$E_{treatment} = \frac{M \cdot \rho - E_{board} \cdot I_{board}}{I_{treatment}}$$

Table 3

Results of bending test performed on boards and results of calculation of elastic modulus of boards and treatments.

Different layers of treated board samples	Drying temperature (°C)	Flexural Elastic Modulus MD (GPa)	Flexural Elastic Modulus CD (GPa)
Layer of virgin board	/	5,08	2,20
Layer of C20G30 on virgin board (applied by brush) 50 ml	60	8,19	6,24
Layer of C80G30 on virgin board (applied by bar)	60	5,64	4,62
Layer of Recycled board	/	4,21	1,99
Layer C80G30 on recycled board (applied by bar)	60	7,92	4,18
Layer C80G30 on recycled board (applied by bar)	110	6,48	4,52

Treatments	Bacteria (UFC/m ²)	Molds/yeasts (UFC/m ²)
Without treatments	1875	1458
Chitin 2,5%	208	208
Chitin 2,5% + 30 % plast	208	208
Chitosan 2,5% brush	208	833
Chitosan 0,5%/chitin 2%	417	<200
Chitin 2,5%	<200	<200
Chitosan 0,5%/chitin 2% + 30% plast	833	10417

Questo studio conferma l'effetto antimicrobico di chitina e chitosano per l'applicazione su imballaggi in carta. In particolare, la chitina è più efficace come antimicrobico rispetto al chitosano, specialmente contro muffe e lieviti. Inoltre, l'aggiunta di plastificante in alcuni casi aumenta la proliferazione di microrganismi.

batteri   muffe/lieviti

Without treatments

UFC/m²=1875

UFC/m²=1458

Chitin 2,5%

UFC/m²=208

UFC/m²=208

Chitin 2,5% + 30 % glycerol

UFC/m²=208

UFC/m²=208

Chitosan 2,5%

UFC/m²=208

UFC/m²=833

batteri   muffe/lieviti

Chitosan 0,5%/chitin 2%

UFC/m²=417

UFC/m²<200

brush

Chitin 2,5%

UFC/m²<200

UFC/m²<200

Chitosan 0,5%/chitin 2% + 30% glicerolo

UFC/m²=833

UFC/m²=10417

Chitosan and nano-structured chitin for biobased anti-microbial treatments onto cellulose based materials
Luca Panariello^a, Maria-Beatrice Coltelli^{a,b}, Marco Buchignani^c, Andrea Lazzeri^{a,b,*}

TEST MICROBIOLOGICI SUL CIBO

> Shelf life !!!!

Recycled paperboard

perché non applicare su substrati
cellulosici dei film a base
bioplastica contenenti CN ?

***N-CHITOPACK** - Sustainable technologies for the production of biodegradable materials based on natural chitin-nanofibrils derived by waste of fish industry, to produce food grade packaging, **Research for the benefit of SME**, 01.11.2012-31.10.2014, European FP7 project*

Per ottenerli alcuni studi sono
stati effettuati nell'ambito del
progetto europeo **NANO-
CHITOPACK**

Dispersione delle CN nel biopoliestere allo stato fuso

Pre-composito preparato con PEG e CN

(a)

(b)

miniestrusore

POLI(ACIDO LATTICO) (PLA)

(a)

(b)

Mini injection molding press

	E (GPa)	s_b (MPa)	e_b (%)
PLA	3.5 ± 0.1	60.4 ± 0.3	4.1 ± 0.5
PLA+2CN*	2.9 ± 0.1	58.0 ± 2.0	2.3 ± 0.4
PLA +P4-10	2.3 ± 0.3	33.0 ± 2.0	180.0 ± 10.0
PLA+P4-10+2CN	1.8 ± 0.3	32.0 ± 2.0	160.0 ± 10.0
PLA+P80-10+2CN	2.5 ± 0.1	34.0 ± 2.0	160.0 ± 10.0

Thermal properties : DSC

	T_g (°C)	T_{cc} (°C)	DH _{cc} (J/g)	T_m (°C)	DH _m (J/g)
PLA	59.1	109.4	23.8	148.3/157,4	2.6
PLA+2CN*	55.2	108.8	23.3	147.9/155,8	1.2
PLA + P4-10	36.1	83.8	21.3	153.7	11.3
PLA+P4-10+2CN	32.7	79.8	17.1	152.1	12.1
PLA+P80-10+2CN	31.4	80.5	17.5	154.2	11.8

Sebbene i CN non abbiano migliorato il modulo elastico e lo stress a rottura, il mantenimento di un elevato allungamento a rottura indica che è stata ottenuta una dispersione sulla nanoscala, in accordo con le valutazioni morfologiche e ottiche.

Le proprietà termiche non vengono influenzate significativamente dalla presenza delle CN

International Journal of
Molecular Sciences

Article

Chitin Nanofibrils in Poly(Lactic Acid) (PLA) Nanocomposites: Dispersion and Thermo-Mechanical Properties

Maria-Beatrice Coltelli^{1,2,*} , Patrizia Cinelli^{1,2}, Vito Gigante^{1,2}, Laura Aliotta^{1,2} , Pierfrancesco Morganti^{3,4}, Luca Panariello^{1,2} and Andrea Lazzeri^{1,2,*}

Advanced Materials Letters

Research Article

2019, 10(6), 425-430

Advanced Materials Letters

Chitin Nanofibrils in Renewable Materials for Packaging and Personal Care Applications

Maria-Beatrice Coltelli^{1,2*}, Vito Gigante^{1,2}, Luca Panariello^{1,2}, Laura Aliotta^{1,2}, Pierfrancesco Morganti³, Serena Danti^{1,2}, Patrizia Cinelli^{1,2}, Andrea Lazzeri^{1,2}

CHEMICAL ENGINEERING TRANSACTIONS

VOL. 60, 2017

Guest Editors: Luca Di Palma, Elisabetta Petrucci, Marco Stoller
Copyright © 2017, AIDIC Servizi S.r.l.
ISBN 978-88-95608-50-1; ISSN 2283-9216

The Italian Association
of Chemical Engineering
Online at www.aidic.it/ceet

Degradability and Sustainability of Nanocomposites Based on Polylactic Acid and Chitin Nano Fibrils

Patrizia Cinelli^a, Maria Beatrice Coltelli^a, Norma Mallegni^a, Pierfrancesco Morganti^b, Andrea Lazzeri^a

waste food

chitin nanofibrils

Renewable plastic pellets

Injection molding

Blow extrusion

Flat die extrusion

Questi risultati possono aprire la strada allo sviluppo di nanocompositi funzionali contenenti queste nanofibrille antimicrobiche e rigenerative, adatte per essere utilizzate in una vasta gamma di applicazioni (imballaggio, cura della persona e biomedicina).

OBIETTIVI DI POLYBIOSKIN

La visione del progetto PolyBioSkin è di incrementare l'uso di biopolimeri che offrono attività antimicrobica, antiossidante, assorbente, compatibilità cutanea in applicazioni strategiche ed esigenti per il contatto con la pelle (pannolini, maschere facciali e medicazioni):

- miglioramento della qualità della vita e del benessere;
- riduzione dell'impatto ambientale e opzioni di fine vita più sostenibili;
- maggiore competitività dei settori europeo sanitario, cosmetico e biomedico.

>90% di contenuto bio-based in tutte le applicazioni

Nell'ambito di questo progetto è stato dimostrato che le nanofibrille chitina e le miscele di biopoliestere non riducono la vitalità delle cellule della pelle

Sono stati formulati film di biopoliesteri con le proprietà necessarie per il **topsheet**.

	F1 MD	F1 CD	F2 MD	F2 CD
E (GPa)	≈ 0.140	≈0.111	≈0.080	≈0.080
σ_b (MPa)	21 ± 3	16 ± 1	20 ± 6	25.1 ± 5.5
ϵ_b (%)	380 ± 30	33 ± 20	410 ± 30	423.2 ± 46.1

La compatibilità dei film con cheratinociti e cellule staminali mesenchimali è stata trovata molto buona, con una leggera azione antimicrobica dovuta all'attivazione di defensine

Attività in corso sull'uso di CN nei film

Aggiungere CN per funzionalizzare i film per topsheet

2 pre-compositi :

- Spray dried 98:2 CN/PEG powder
- Pre-composito 50:50 CN/PEG

blend	E (GPa)	σ_b (MPa)	ϵ_b (%)
PLA pure	3,5	61,4	2,7
PLA + 2% CN	3,5	48	1,60
PLA70/P30 + 20%ATBC	0,3	16,8	210
PLA70/P30 + 2% CN + 20%ATBC	0,68	13,9	264
PLA70/P30 +4%nc(50)+18%ATBC	0,13	20,1	490
PLA70/P30 +4%nc(50)+16%atbc+2%bioS	0,15	21,1	335,4
PLA70/P30 +4%nc(50)+14%atbc+4%bioS	0,10	19,1	370

Uso di un melt strength enhancer

Test anti-microbici preliminari hanno mostrato che non c'è una attività anti-microbica, probabilmente perché CN è scarsamente presente sulla superficie del film → COATING

Modifiche funzionali grazie ad una piattaforma di biopolimeri e complessi

Composti attivi possono essere intrappolati nei complessi chitina/lignina

Prove di stabilità termica e compatibilità con i cheratinociti hanno portato alla selezione dei migliori trattamenti per le tre diverse applicazioni del progetto POLYBIOSKIN

Proprietà barriera: il progetto BIOBOARD

BIO-BOARD deals with the “Development of sustainable protein-based paper and paperboard coating systems to increase the recyclability of food and beverage packaging.

Research for the benefit of SME AGs, 01.11.2012-31.10.2015

Research activity: Production of sustainable plastic films containing protein derived by whey and potato by products.

Whey protein coating can provide biodegradable plastic layers that can replace existing plastic coatings in multilayer packaging and enhance their recyclability –by separating the individual fractions of the multilayer packaging.

Whey proteins

By-product of cheese production containing 7% dry matter of which 13% proteins, 75% lactose, 8% minerals, 3% organic acids and 1% fat

Whey protein can be separated and purified by membrane filtration process followed by spray drying

- 40-50% of the 50 million tons of whey produced annually in Europe is discarded
- Finding a new value added use is of interest for dairy producers

Preparation of biobased blends and composites

Polymer-Plastics Technology and Engineering

ISSN: 0360-2559 (Print) 1525-6111 (Online) Journal homepage: <http://www.tandfonline.com/loi/lpte20>

Effect of Potato Pulp Filler on the Mechanical Properties and Water Vapor Transmission Rate of Thermoplastic WPI/PBS Blends

Markus Schmid, Carola Herbst, Kerstin Müller, Andreas Stäbler, Daniel Schlemmer, Maria-Beatrice Coltelli & Andrea Lazzeri

Potato pulp

The potato pulp forms aggregates

paper

BB51BΦ

juice

210115-1
Juice (low/medium barrier)
BB51BΦ

material	thickness / board weight	Process steps dry lamination
PE	30µm	4
ASL 120	5 µm	4
Epotal	5-10 µm	3
BB 51	280 - 300 µm	1
Epotal	5-10 µm	1
board	180 gsm	1
Epotal	5-10 µm	2
PE	30 µm	2

Review

State of the Art in the Development and Properties of Protein-Based Films and Coatings and Their Applicability to Cellulose Based Products: An Extensive Review

Maria-Beatrice Coltelli ^{1,*}, Florian Wild ^{2,*}, Elodie Bugnicourt ^{3,*}, Patrizia Cinelli ¹, Martina Lindner ², Markus Schmid ^{2,4}, Verena Weckel ², Kerstin Müller ², Pablo Rodriguez ², Andreas Staebler ², Laura Rodríguez-Turiénzo ³ and Andrea Lazzeri ¹

ECO sustainable multifunctional biobased COATings with enhanced performance and end of life options GA 837863, BBI2018-RIA-A

UNIVERSITY OF WESTMINSTER

Universitat d'Alacant / Universidad de Alicante

TURKEY
ORGK - Large

ISRAEL
TIPA - SME

ITALY
INSTM - RTD
SSICA - RTD
LUCENSE - RTD
PLABIO - SME
ARCHA - SME
CPP - SME

BELGIUM
CELABOR - SME

GERMANY
FHF - RTD
HWH Large

CROATIA
BIO-MI - SME

SPAIN
UA - RTD
KNEIA - SME
IRIS - SME
CQSA - SME

ECOAT STRATEGY

$$\left(\text{HO} \begin{array}{c} \text{HO} \\ | \\ \text{C} \\ | \\ \text{O} \end{array} \text{---} \text{C} \begin{array}{c} \text{HO} \\ | \\ \text{C} \\ | \\ \text{O} \end{array} \text{---} \right)_n$$
 Chitin

$$\left(\text{HO} \begin{array}{c} \text{HO} \\ | \\ \text{C} \\ | \\ \text{O} \end{array} \text{---} \text{C} \begin{array}{c} \text{H}_2\text{N} \\ | \\ \text{C} \\ | \\ \text{O} \end{array} \text{---} \right)_n$$
 Chitosan

C₁₆ Acids

$\text{CH}_3(\text{CH}_2)_{14}\text{COOH}$

$\text{CH}_2(\text{CH}_2)_{14}\text{COOH}$

$\text{CH}_2(\text{CH}_2)_x\text{CH}(\text{CH}_2)_y\text{COOH}$

$y = 5, 6, 7, \text{ or } 8, \text{ and } x + y = 13$

C₁₈ Acids

$\text{CH}_3(\text{CH}_2)_7\text{CH}=\text{CH}(\text{CH}_2)_7\text{COOH}$

$\text{CH}_2(\text{CH}_2)_7\text{CH}=\text{CH}(\text{CH}_2)_7\text{COOH}$

$\text{CH}_2(\text{CH}_2)_7\text{CH} \begin{array}{c} \diagup \\ \diagdown \end{array} \text{CH}(\text{CH}_2)_7\text{COOH}$

$\text{CH}_2(\text{CH}_2)_7\text{CH} \begin{array}{c} \diagup \\ \diagdown \end{array} \text{CH}(\text{CH}_2)_7\text{COOH}$

Cutin-forming acids

The protein
molecular structure of the protein

- Chlorine
- Carbon
- Nitrogen
- Amino acid side chain
- Hydrogen

Our Research Team

Interdepartmental Center of
Materials Science and Engineering

Full Professor

Dott. Ing. Andrea Lazzeri

MATERIALS AND NANOTECHNOLOGY

Corso di laurea magistrale

Associate and Assistant Professors

Patrizia Cinelli – Maria Beatrice Coltelli – Serena Danti

Researchers, Post Docs, PhDs, Research Grants

Francesca Signori

Luca Panariello

Laura Aliotta

Bahareh Azimi

Vito Gigante

Alessandro Vannozzi

EUROPEAN NETWORK of MATERIALS RESEARCH CENTRES

www.enmat.eu

President of ENMat:
Dr. Maria Beatrice COLTELLI
Centre for Materials Science and
Engineering (CISIM),
University of Pisa, Italy

IMBALLAGGI ECO-SOSTENIBILI PER IL CONTATTO ALIMENTARE

Benefits for members

- ◆ **Contacts** with materials research centres all over Europe
- ◆ Platform for **partner search**: find academic and industrial project partners
- ◆ **Promotion and publicity** of activities and achievements on a European and global stage

ENMAT is open to all multidisciplinary research centres in materials sciences in Western and Eastern Europe.

Candidate members have to meet the following criteria:

- ◆ Multidisciplinary research centre in materials science: academic or research centre or industrial network dealing with materials in a broader sense

- ◆ Having high quality & competences in materials science

- ◆ Being active in research & development

- ◆ Play a role in materials education (of students and/or industry)

- ◆ Being active in technology transfer

- ◆ Be prepared to participate in joint projects (also with industry)

Issue 5, March 2018

European Network of Materials Research Centres

NEWSLETTER

Breakthrough of new Networking between European Materials Research Centres

Welcome

Welcome to the fifth issue of ENMat Newsletter. ENMat has been founded in September 2005, to create a powerful network of leading Materials Research Centres in Europe. We expect to stimulate beneficial interdisciplinary activities between members of the network as well as to increase the efficiency of the transfer of results from R&D to industry. We also expect to improve opportunities for participation in activities in the frame of EU supported projects.

Highlights in this Newsletter

Description of ENMat members: **FRANZHOFER IKTS** (Germany) and **IMT Mines Ales/C2MA** (France) - page 2

CERAMIC MATERIALS RESEARCH IN EUROPE - page 3

Members

- Centre des Matériaux des Mines d'Ales (C2MA), Ecole des Mines d'Ales, Ales Cedex, France
- Centre for Materials Science and Engineering (CMSEL), Pisa, Italy

Grazie per la vostra attenzione!!!